

Technical data sheet PC

Ultimaker
It's in the making

Chemical Name	Polycarbonate
Description	With Ultimaker PC filament, you can print strong and tough parts that retain dimensional stability when subjected to temperatures as high as 110oC. Our PC is engineered to be printed at moderate temperatures compared to other PC filaments and shows minimized warping providing a seamless 3D printing experience.
Key features	High toughness (especially for the non-transparent filament options), resists temperatures and retains form up to 110oC, flame retardant characteristics, dimensionally stable, strong interlayer bonding (especially when using the front door add-on), good bed adhesion (especially when using the Avery stickers). Allows printing of translucent parts with the transparent filament option.
Applications	Lighting, molds, engineering parts, tools, functional prototyping and short run manufacturing.
Non suitable for	Food contact and in-vivo applications.

Filament specifications

	<u>Value</u>	<u>Method</u>
Diameter	2.85±0.05 mm	Ultra-fast CCS-based, dual-axis diameter gauge
Max roundness deviation	0.05 mm	Ultra-fast CCS-based, dual-axis diameter gauge
Net filament weight	750 g	-

Color information

<u>Color</u>	<u>Color code</u>
PC Transparent	n/a
PC Black	RAL 9005
PC White	RAL 9003

Mechanical properties (*)(**)

Injection molding

3D printing

	<u>Typical value</u>	<u>Test method</u>	<u>Typical value</u>	<u>Test method</u>
Tensile modulus	-	-	2307 MPa (t) 2048 MPa (b/w)	ASTM D638
Tensile stress at yield	-	-	-	-
Tensile stress at break	-	-	62.7 MPa (t) 59.7 MPa (b/w)	ASTM D638
Elongation at yield	-	-	-	-
Elongation at break	-	-	3.15% (t) 12.24% (b/w)	ASTM D638
Flexural strength	-	-	100.4 MPa (t) 94.1 MPa (b/w)	ASTM D790
Flexural modulus	-	-	2477 MPa (t) 2044 MPa (b/w)	ASTM D790
Izod impact strength, notched (at 23°C)	-	-	-	-
Charpy impact strength (at 23°C)	-	-	3.41 kJ/m ² (t) 25.1 kJ/m ² (b/w)	ASTM D256
Hardness	-	-	-	-

Thermal properties

Typical value

Test method

Melt mass-flow rate (MFR)	32 - 35 g/10 min (t) 23 - 26 g/10 min (b/w)	(300 °C, 1.2 kg)
Heat deflection (HDT) at 0.455 MPa	-	-
Heat deflection (HDT) at 1.82 MPa	-	-
Glass transition	112 - 113 °C	DSC, 10 °C/min
Coefficient of thermal expansion (flow)	-	-
Coefficient of thermal expansion (xflow)	-	-
Melting temperature	-	-
Thermal shrinkage	-	-

Other properties

Typical value

Test method

Specific gravity	1.18 -1.20	ASTM D792
Flame classification	-	-

(*) See notes.

(**) t: transparent. b/w: black/white.

Notes

Properties reported here are average of a typical batch. The mechanical properties are from specimens printed flat at 100% infill under 45°, 2 shells, 0% fan speed, middle of the bed, nozzle temperature 255 °C, bed temperature 80 °C, BuildTak sheet on the bed, nozzle diameter 0.4 mm, all print speeds are 60 mm/s, and layer height 0.2 mm. Ultimaker is constantly working on extending the TDS data.

Disclaimer

Any technical information or assistance provided herein is given and accepted at your risk, and neither the Ultimaker or its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale. Specifications are subject to change without notice.

Version

Version 3.003

Date

19/10/2016

Ultimaker
It's in the making